
PEROXAN ME-50 LS-P 10 X

Ketone peroxide / Curing

Description

Methyl ethyl ketone peroxide
Solution in TXIB

PEROXAN ME-50 LS-P 10 X is used for the curing of unsaturated polyester at ambient temperature in combination with cobalt accelerators.



CAS No.:	**1338-23-4**

Technical data

Appearance:	**clear liquid**
Active oxygen assay:	**9.7%**
Density at 20°C:	**1.015 g/cm³**

Solubility

Insoluble in water

Storage

Maximum storage temperature (Ts max):	**30°C**
Minimum storage temperature (Ts min):	**0°C**
Storage stability as from date of delivery:	**6 months**

Hazardous reactions

Keep packaging tightly closed in a well ventilated place at indicated storage temperature. Keep away from reducing agents e.g. amines, acids, alkalis, heavy metal compounds (e.g. accelerators, driers, metal soaps). Never weigh out in storage room.

Oxidizing agent. Decomposes violently under the influence of heat or by contact with reducing agent. Never mix with accelerators.

Safety characteristics

Flash point:	>55°C
SADT:	60°C

The SADT (Self Accelerating Decomposition Temperature) is the lowest temperature at which a self accelerating decomposition may occur.

PERGAN The Peroxide Company
Schlavenhorst 71
D-46395 Bocholt
Germany
Phone: +49 (0)2871 / 99 02-0
Fax: +49 (0)2871 / 99 02-50
www.pergan.com

PEROXAN ME-50 LS-P 10 X

Ketone peroxide / Curing

Application

PEROXAN ME-50 LS-P 10 X is used for the curing of unsaturated polyester resins at ambient temperature in combination with cobalt accelerators.

The curing sytem PEROXAN ME-50 LS-P 10 X and Cobalt accelerator is particularly suitable for the curing of laminating resins and lacquers when a faster gelation and initial cure speed is required than than can be obtained with PEROXAN ME-50 LX; moreover the manufacture of light resistance parts may be possible contrary to the curing system Benzoyl peroxide and Amine accelerator.

Depending on working conditions, the following peroxide and accelerator dosage levels are recommended:

PEROXAN ME-50 LS-P 10 X: 1,0 to 4,0 phr
PERGAQUICK C12 X (Cobalt, 1%): 0,5 to 3,0 phr

Packaging

30kg container

Major decomposition products

Formic acid, Acetic acid, Carbon dioxide, Methylethylketon, Propionic acid, Water

Safety and handling

Please refer to the material safety data sheet (MSDS) for information concerning safe storage, use and handling of PEROXAN ME-50 LS-P 10 X. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available for downloading at **www.pergan.com** or through contacting Pergan directly.

The information presented herein is true and accurate and to the best of our knowledge, but without any guarantee. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestions.

Schlavenhorst 71
D-46395 Bocholt
Germany

Phone: +49 (0)2871 / 99 02-0
Fax: +49 (0)2871 / 99 02-50
www.pergan.com